

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

Imocave Pty Ltd
Attn: Callum Wass
1 Conway Court
Nerang
QLD 4211
AUSTRALIA

18/06/2021

Dear Callum,

Please find the attached report to AS/NZS 4020:2018 for RTT Sealant Water Proofing Membrane submitted for testing.

Should you have any enquiries about the report or any other matters pertaining to the Standard please contact the laboratory on 61 8 7424 1512

Yours sincerely,

Michael Glasson
Supervisor Product Testing



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

Report Information

Submitting Organisation : 00121181 : Imocave Pty Ltd
Account : 142139 : Imocave Pty Ltd
AWQC Reference : 142139-2020-CSR-1 : Prod Test
Project Reference : PT-4378
Product Designation : RTT Sealant Water Proofing Membrane
Composition of Product : Elastomeric Liquid Rubber Membrane (Waterproofing).
Product Manufacturer : Imocave Pty Ltd TA RTT Sealant, Nerang, QLD, AUSTRALIA.
Use of Product : In-Line/Waterproofing Membrane.
Sample Selection: As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018
Extracts : Extracts were prepared as described in Appendix/Clause C, D, E, F, G, H, 6.8.
Project Completion Date : 23-Dec-2020
Project Comment : The results presented herein demonstrate compliance of RTT Sealant Water Proofing Membrane to AS/NZS 4020 when exposed at area to volume ratios up to 7500 mm²/L at 20°C ± 2°C.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER

Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 311610

Summary of Results

APPENDIX/CLAUSE	RESULTS
C – Taste	Passed at an exposure of 7500 mm ² per Litre.
D – Appearance	Passed at an exposure of 15,000 mm ² per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 13,350 mm ² per Litre with a 0.89 scaling factor applied.
F – Cytotoxic Activity	Passed at an exposure of 15,000 mm ² per Litre.
G – Mutagenic Activity	Passed at an exposure of 15,000 mm ² per Litre.
H – Metals	Passed at an exposure of 15,000 mm ² per Litre.
6.8 – Organic Compounds	Passed at an exposure of 15,000 mm ² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2120c & APHA 2130b
E	TO014-03	APHA 4500 O G
F	TM-001	AS/NZS 4020:2018
G	TM-002	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

Summary Comment : Waterproofing membrane applied and cured for 7 days at 20°C prior to testing.



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.2 Taste

Sample Description The sample consisted of a single coated panel with dimensions 75 mm x 100 mm providing a total surface area of approximately 7500 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Taste (Appendix C)

Test Information

Scaling Factor Not applicable.

Results Not detected (sample and controls).

Evaluation The product passed the requirements of clause 6.2 when tested at an exposure of 7500 mm² per Litre.

Number of Samples 4.

Test Comment Panellists detected chemical tastes in the final (7th) chlorinated extracts when tested at an exposure of 13,350mm²/L (20°C). Test repeated at 7500mm²/L (20°C) where no tastes were detected.

Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.3 Appearance

Sample Description The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Appearance (Appendix D)

Scaling Factor Not applicable.

Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 15,000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Dzung Bui
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor A scaling factor of 0.89 was applied.

Results

Mean Dissolved Oxygen	Control	7.5 mg/L
Mean Dissolved Oxygen Difference	Positive Reference	5.2 mg/L
	Negative Reference	<0.1 mg/L
	Test	2.40 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 13,350 mm² per Litre with a 0.89 scaling factor applied.

Number of Samples 1.

Test Comment The arithmetic mean of nine dissolved oxygen values exceeded the maximum allowable concentration for MDOD. A scaling factor of 0.89 was applied to meet the requirements of Clause 6.4.

Aji John
APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.5 Cytotoxic Activity

Sample Description The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Cytotoxic Activity (Appendix F)

Scaling Factor Not applicable.

Results Non-cytotoxic (sample and controls).

Evaluation The product passed the requirements of clause 6.5 when tested at an exposure of 15,000 mm² per Litre.

Number of Samples 1.

Test Comment The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.

Mira Maric

APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.6 Mutagenic Activity

Sample Description The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Mutagenic Activity (Appendix G)

Scaling Factor Not applicable.

Results

	<u>Bacteria Strain</u>		<u>Number of Revertants per Plate</u>		
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	29, 26, 29	19, 25, 25	3894, 4301, 4158	<u>NPD</u> (20µg)
Mean ± Standard deviation		28.0 ± 1.7	23.0 ± 3.5	4117.7 ± 206.5	
	+	39, 41, 28	25, 19, 32	3243, 3764, 3081	<u>2-AF</u> (20µg)
Mean ± Standard deviation		36.0 ± 7.0	25.3 ± 6.5	3362.7 ± 356.9	
<i>Salmonella typhimurium</i> TA102	-	404, 475, 455	443, 463, 514	3466, 2473, 2518	<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		444.7 ± 36.6	473.3 ± 36.6	2819.0 ± 560.8	
	+	572, 584, 584	431, 467, 502	2029, 1856, 2071	
Mean ± Standard deviation		580.0 ± 6.9	466.7 ± 35.5	1985.3 ± 114.0	

Comments S9 was used as the metabolic activator. NPD (4-nitro-o-phenylenediamine) and Mitomycin C are specific positive controls for strains TA98 - and TA102 (- and +) respectively, while 2-AF (2-aminofluorene) when used in conjunction with S9 is a positive control for TA98+.

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 15,000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Dzung Bui
APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

CLAUSE 6.7

Metals

Sample Description

The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Metals (Appendix H)

Scaling Factor

Not applicable.

Method of Analysis

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.004	0.008	0.008	0.2
Antimony	0.0005	<0.0005	0.0007	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.01
Barium	0.0005	<0.0005	<0.0005	0.0005	0.7
Boron	0.020	<0.020	<0.020	<0.020	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	<0.0001	<0.0001	<0.0001	2.0
Iron	0.0005	<0.0005	<0.0005	<0.0005	0.3
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Manganese	0.0001	<0.0001	<0.0001	<0.0001	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation

The product passed the requirements of clause 6.7 when tested at an exposure of 15,000 mm² per Litre.

Number of Samples

1.

Test Comment

Not applicable.

Andrew Ford

APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 311610

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of two coated panels (to one side each) with dimensions 75 mm x 100 mm providing a total surface area of approximately 15,000 mm²/L. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

Scaling Factor Not applicable.

Results

Organic Compound

Nitrosamines	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	0.004	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

Organic Compound

Phenols	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 µg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 µg/L
phenol	<1.0	<1.0	



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

Organic Compound

Phthalate Esters

	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

Organic Compound

Polycyclic Aromatic Hydrocarbons

	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2035008	ES2035008	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
Volatile Organic Compounds GCMS			
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	<1	<1	60 µg/L
Bromoform	<1	<1	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	<1	<1	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	<1	<1	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	<1	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	<2	



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025





Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 311610

Organic Compound

Organic Compound	Blank µg/L	Test µg/L	Max Allowed
Volatile Organic Compounds GCMS			
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	<1	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	<1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	<3	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	<4	<4	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 15,000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.

Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No. 1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

